

# Promat

## Promat<sup>®</sup> PSK 101

Water Based Synthetic Latex, Sealer and Keycoat

Promat FENDOLITE<sup>®</sup>-MII Integrated Fire Protective Coating System



### PROPERTIES AND PERFORMANCES

|                                  |   |
|----------------------------------|---|
| <b>Colour and finish</b>         | Dark green (nearest to BS 4800: 1981, colour code 10 B 25).<br>May be applied by spray, roller or brush   |
| <b>Typical thickness</b>         | 100-150 microns wet film thickness (WFT)<br>Do not apply less than 100 microns<br>55-82 microns dry film thickness (DFT)  |
| <b>Practical coverage</b>        | Dependent on surface texture, substrate porosity, application method and technique  |
| <b>Theoretical coverage</b>      | 8m <sup>2</sup> /litre at 125 microns WFT   |
| <b>Number of coats</b>           | One or more as required dependent on application technique.<br>May be recoated once previous coat is touch dry  |
| <b>Maximum over coating time</b> | 2 months with either more Promat <sup>®</sup> PSK 101 or Promat FENDOLITE <sup>®</sup> -MII   |
| <b>Cure</b>                      | By air drying   |
| <b>Drying time</b>               | Touch dry ½ to 1 hour at 20°C and 50% RH<br>Fully dry 2 to 6 hours at 20°C and 50% RH<br>Varies with ambient conditions, but high humidity, low temperature and low air change will hinder cure significantly |
| <b>Solids by weight</b>          | 55%   |
| <b>Weight</b>                    | 1.25kg/litre  |

### Advantages

- Strongly bonded integrated coating system
- Excellent capability & durability

### Introduction

Promat<sup>®</sup> PSK 101 is a single pack, multi purpose water based synthetic latex emulsion for use as a sealer and keycoat as a component of the Promat FENDOLITE<sup>®</sup>-MII integrated fire protective coating system.

Promat<sup>®</sup> PSK 101 is suitable for on site or off site application to construction elements such as steel or concrete sections and metal decks.

Onshore oil and gas, petrochemical and power industries will benefit from the use of Promat<sup>®</sup> PSK 101.

### Quality assurance

Promat products are manufactured to stringent quality control systems to assure that our customers receive materials made to the highest standards.

Operating to these standards means that all activities, which have a bearing upon quality, are set out in written procedures.

Systematic and thorough checks are made on all materials and their usage. Test equipment is subjected to regular checks and is referred back to national standards.

The information given in this data sheet is based on actual tests and is believed to be typical of the product. No guarantee of results is implied however, since conditions of use are beyond our control.

### Health and safety

Adequate ventilation must be provided during use. Avoid contact with the skin and eyes by using eye protection, gloves, barrier cream and a face mask.

If the product comes into contact with the skin, wash immediately with soap and water. If the eyes are affected, flush with plenty of water and seek medical attention immediately.

A safety data sheet is available from Promat upon request.

Promat activities are conducted with due regard to all statutory requirements with appropriate safeguards against exposing employees and the public to health and safety risks.

### Preparation

#### Typical substrates

Unprimed or primed steel

#### Substrate preparation

The substrate must be clean, dry and free from dust, loose millscale, loose rust, oil, visible moisture (including condensation) and any other condition preventing good adhesion.

### Application

#### Initial steps

Stir contents before use. Do not thin.

#### Methods

Promat® PSK 101 may be applied with an industrial type airless or airassisted spray, or lambswool roller. It may also be applied with a brush in small (maximum 1m<sup>2</sup>) areas only.

#### Limitations

Promat® PSK 101 may be applied when the substrate and air temperatures are at least 2°C and rising.

Maximum air and substrate temperature is 45°C. Substrate temperature should be at least 2°C above dew point temperature.

Protect from rain, hail etc until dry.

### Packaging

20 litre metal pails.

### Storage

Protect from frost, excessive heat (above 45°C) and strong radiant sunlight.

### Shelf life

Max. 12 months.

### Environmental

Do not discharge into drains, watercourses or soil.

All specified technical data are mean values from the production which are subject to the usual fluctuations and do not represent guaranteed properties in the sense of a guarantee. All information corresponds to the current state of the art and has been presented and described to the best of our knowledge. Changes due to new findings are possible, errors and misprints are not excluded. With regard to any liability, our delivery and payment terms apply exclusively. Request safety datasheet. With the publication of this edition, all previously published datasheets are invalid. © Copyright Etex NV, Brussels, Belgium. All rights reserved. 2020-10

Etex Industry c/o Microtherm N.V., Industriepark-Noord 1, 9100 Sint-Niklaas, Belgium | T +32 (0)3 760 19 80 | F +32 (0)3 760 19 99  
industry@promat.com | www.promat.com/industry